

NORMAS: - ASTMA 240 - 06C, NOVIEMBRE 2006  
 - EN 10088-2, SEPTIEMBRE 2005  
 - JIS G 4305, 1991

## GRUPO 1

	alSi, aSTm	composición química (Peso máximo %)													norma	ref.
		c	Si	mn	P	S	cr	mo	Ti	nb	cu	al	n	ni		
10%-14%cr	403(M)	0.15 0.12-0.17	0.5 1.0	1.0 1.0	0.04 0.04	0.03 0.015	11.5-13.0 12.0-14.0								JIS EN	SUS403 1.4024
	405	0.08 0.08 0.08 0.08	1.0 1.0 1.0 1.0	1.0 1.0 1.0 1.0	0.04 0.04 0.04 0.04	0.03 0.015 0.015 0.03	11.5-14.5 12.0-14.0 12.0-14.0 11.5-14.5				0.1-0.3 0.1-0.3 0.1-0.3		0.6	UNS EN EN JIS	S40500 1.4000 1.4002 SUS405	
	409L	0.03 0.03 0.03 0.03 0.03 0.03 0.03 0.03 0.03 0.03	1.0 1.0 1.0 1.0 1.0 1.0 1.0 1.0 1.0 1.0	1.0 1.0 1.0 1.0 1.0 1.5 1.0 1.0 1.5 1.0	0.04 0.04 0.04 0.04 0.04 0.04 0.04 0.04 0.04 0.04	0.02 0.02 0.02 0.02 0.02 0.015 0.015 0.015 0.015 0.03	10.5-11.7 10.5-11.7 10.5-11.7 10.5-11.7 10.5-11.7 10.5-12.5 10.5-12.5 10.5-12.5 10.5-12.5 10.5-11.75		6x(C+N)-0.5 8x(C+N)-0.5 [0.08+8x(C+N)]-0.75 0.05-0.2 6x(C+N)-0.75	0.17 0.1 0.18-0.4		0.03 0.03 0.03 0.03 0.03 0.5-1.0 0.3-1.0 0.5 0.5-1.5 0.6	0.5 0.5 0.5 0.5 0.5 0.5 0.5 0.5 0.5 0.5	UNS UNS UNS UNS UNS UNS UNS UNS UNS JIS	S40910 S40920 S40930 S40945 S40975 S40977 S40977 S40977 S40977 SUH409L	
	410(M)	0.08-0.15 0.08-0.15 0.15	1.0 1.0 1.0	1.0 1.5 1.0	0.04 0.04 0.04	0.03 0.015 0.03	11.5-13.5 11.5-13.5 11.5-13.5						0.75 0.75	UNS EN JIS	S41000 1.4006 SUS410	
	410L	0.03 0.03 0.04 0.03	1.0 1.0 1.0 1.0	1.5 1.0 1.0 1.0	0.04 0.04 0.045 0.04	0.03 0.03 0.03 0.03	10.5-12.5 12.0-13.0 10.5-12.5 11.0-13.5		9(C+N)-0.6		0.03 0.03 0.1	1.5 0.5 0.6-1.10	UNS UNS UNS JIS	S41003 S41045 S41050 SUS410L		
		0.03	1.0	1.5	0.04	0.015	10.5-12.5						0.3-1.0	EN	1.4003	
	410S(M)	0.08 0.08	1.0 1.0	1.0 1.0	0.04 0.04	0.03 0.03	11.5-13.5 11.5-13.5						0.6 0.6	UNS JIS	S41008 SUS410S	
	420J1(M)	0.16-0.25 0.16-0.25	1.0 1.0	1.0 1.5	0.04 0.04	0.03 0.015	12.0-14.0 12.0-14.0							JIS EN	SUS420J1 1.4021	
	420J2(M)	0.26-0.40 0.26-0.35 0.36-0.42 0.43-0.50	1.0 1.0 1.0 1.0	1.0 1.5 1.0 1.0	0.04 0.04 0.04 0.04	0.03 0.015 0.015 0.015	12.0-14.0 12.0-14.0 12.5-14.5 12.5-14.5							JIS EN EN EN	SUS420J2 1.4028 1.4031 1.4034	

## GRUPO 2

	alSi, aSTm	composición química (Peso máximo %)													norma	ref.
		c	Si	mn	P	S	cr	mo	Ti	nb	cu	al	n	ni		
14%-18%cr	420	0.08 0.08	1.0 1.0	1.0 1.0	0.045 0.04	0.03 0.015	13.5-15.5 13.5-15.5	0.2-1.2 0.2-1.2	0.3-0.5 0.3-0.5					1.0-2.5 1.0-2.5	UNS EN	S42035 1.4589
	429	0.12 0.12	1.0 1.0	1.0 1.0	0.04 0.04	0.03 0.03	14.0-16.0 14.0-16.0								UNS JIS	S42900 SUS429
	429J1(M)	0.25-0.40	1.0	1.0	0.04	0.03	15.0-17.0								JIS	SUS429J1
	430	0.12 0.08 0.12	1.0 1.0 0.75	1.0 1.0 1.0	0.04 0.04 0.04	0.03 0.015 0.03	16.0-18.0 16.0-18.0 16.0-18.0						0.75	UNS EN JIS	S43000 1.4016 SUS430	
	1.4017	0.08	1.0	1.0	0.04	0.015	16.0-18.0							1.2-1.6	EN	1.4017
	440(M)	0.6-0.75	1.0	1.0	0.04	0.03	16.0-18.0								JIS	SUS440A

### GRUPO 3

	alSI, aSTM	composición química (Peso máximo %)													norma	ref.	
		c	Si	Mn	P	S	Cr	Mo	Ti	Nb	Cu	Al	n	ni			
14%-18% cr estabilizado	430J1L	0.025	1.0	1.0	0.04	0.03	16.0-20.0			8x(C+N)-0.8	0.3-0.8		0.025			JIS	SUS430J1L
	430LX	0.03	0.75	1.0	0.04	0.03	16.0-19.0			0.1-1.0				0.6		JIS	SUS430LX
	439	0.03 0.05	1.0 1.0	1.0 1.0	0.04 0.04	0.03 0.015	17.0-19.0 16.0-18.0		[0.2+4x(C+N)]-1.10 [0.15+4x(C+N)]-0.8			0.15	0.03	0.5		UNS EN	S43035 1.4510
		0.03 0.03 0.03 0.025 0.02	1.0 1.0 1.0 0.5 1.0	1.0 1.0 1.0 0.5 1.0	0.04 0.04 0.04 0.04 0.04	0.03 0.015 0.015 0.015 0.015	17.0-19.0 17.5-18.5 16.0-17.5 16.0-18.0 13.0-15.0		[0.2+4x(C+N)]-0.75 [0.3+(3xC)] 0.35-0.55			0.15	0.03	0.5		UNS UNS UNS EN EN	S43932 S43940 EN 1.4590 EN 1.4520 EN 1.4595
	430Ti	0.05	1.0	1.0	0.4	0.015	16.0-18.0			0.6						EN	1.4511
	441	0.03 0.03	1.0 1.0	1.0 1.0	0.04 0.04	0.03 0.015	17.5-18.5 17.5-18.5		0.1-0.6 0.1-0.6	9xC+0.3-1 3xC+0.3-1				1.0		UNS EN	S44100 1.4509

### GRUPO 4

	alSI, aSTM	composición química (Peso máximo %)													norma	ref.	
		C	Si	Mn	P	S	Cr	Mo	Ti	Nb	Cu	Al	N	Ni	Otros		
mo añadido	415	0.05	0.6	0.5-1.0	0.03	0.03	11.5-14.0	0.5-1.0						3.5-5.5		UNS	S41500
	434	0.12 0.08 0.08 0.12	1.0 0.75 1.0 1.0	1.0 0.8 0.04	0.04 0.015 0.015	0.03 0.16-0.18 0.16-0.18	16.0-18.0 0.9-1.4	0.75-1.25 0.8-1.4		[7x(C+N)+0.1]-1.0			0.04			UNS EN EN JIS	S43400 1.4113 1.4526 SUS434
	436	0.12 0.025 0.025	1.0 1.0 1.0	1.0 1.0 0.04	0.04 0.015 0.03	0.03 16.0-18.0 0.75-1.25	16.0-18.0 0.9-1.4	0.75-1.25 0.75-1.25	8x(C+N)-0.8 0.3-0.6 8x(C+N)-0.8			0.025				UNS EN JIS	S43600 1.4513 SUS436L
	1.4419(M)	0.36-0.42	1.0	1.0	0.04	0.015	13.0-14.5	0.6-1.0								EN	1.4419
	1.4110(M)	0.48-0.60	1.0	1.0	0.04	0.015	13.0-15.0	0.5-0.8						V≤0.15		EN	1.4110
	1.4116(M)	0.45-0.55	1.0	1.0	0.04	0.015	14.0-15.0	0.5-0.8						0.1≤V≤0.2		EN	1.4116
	1.4122(M)	0.33-0.45	1.0	1.5	0.04	0.015	15.5-17.5	0.8-1.3						≤1.0		EN	1.4122
	1.4313(M)	≤0.05	0.7	1.5	0.04	0.015	12.0-14.0	0.3-0.7					≥0.02	3.5-4.5		EN	1.4313
	1.4418(M)	≤0.06	0.7	1.5	0.04	0.015	15.0-17.0	0.8-1.5					≥0.02	4.0-6.0		EN	1.4418
otros	436J1L	0.025	1.0	1.0	0.04	0.03	17.0-20.0	0.4-0.8	8x(C+N)-0.8			0.025				JIS	SUS436J1L
	444	0.025 0.025 0.025	1.0 1.0 1.0	0.7-1.5 1.0 0.4	0.04 0.04 0.04	0.03 0.015 0.03	17.5-19.5 17.0-20.0 17.0-20.0	1.75-2.5 1.8-2.5 1.75-2.5	0.2+4(C+N)-0.8 4x(C+N)+0.15-0.8 8x(C+N)-0.8			0.03	1.0		UNS EN JIS	S44400 1.4521 SUS444	

### GRUPO 5

	alSI, aSTM	composición química (Peso máximo %)													norma	ref.	
		c	Si	Mn	P	S	Cr	Mo	Ti	Nb	Cu	Al	n	ni			
otros	445	0.02	1.0	1.0	0.04	0.012	19.0-21.0			10x(C+N)-0.8	0.3-0.6		0.03	0.6		UNS	S44500
	445J1	0.025	1.0	1.0	0.04	0.03	21.0-24.0			0.7-1.5			0.025			JIS	SUS445J1
	445J2	0.025	1.0	1.0	0.04	0.03	21.0-24.0	1.5-2.5					0.025			JIS	SUS445J2
	446	0.06 0.01 0.025 0.03 0.01	0.75 0.4 0.75 1.0 0.4	0.75 0.4 1.0 1.0 0.4	0.04 0.02 0.03 0.03 0.03	0.02 0.02 0.03 0.03 0.02	25.0-27.0 25.0-27.5 24.5-26.0 25.0-28.0 25.0-27.5	0.75-1.5 0.75-1.5 3.5-4.5 3.0-4.0 0.75-1.5	0.2-1.0 0.05-0.2	0.2 0.2	0.04 0.05	0.015 0.035	0.5 3.5-4.5		UNS UNS UNS UNS JIS	S44626 S44627 S44635 S44660 SUSXM27	
	447	0.01 0.03 0.025 0.01	0.2 1.0 1.0 0.4	0.3 0.04 0.03 0.03	0.025 0.03 0.02 0.02	0.02 0.03 0.01 0.02	28.0-30.0 28.0-30.0 28.0-30.0 28.5-32.0	3.5-4.2 3.6-4.2 3.5-4.5 1.5-2.5	6x(C+N)-1.0 [4x(C+N)+0.15]-0.8	0.15	0.02 0.045 0.045 0.015	0.15 1.0 0.025	(C+N) 0.025 1.0 0.025 0.015		UNS UNS EN JIS	S44700 S44735 1.4592 SUS447J1	
	448	0.01	0.2	0.3	0.025	0.02	28.0-30.0	3.5-4.2			0.15		0.02	2-2.5	(C+N) 0.025	UNS	S44800